



明達漆業(星)私人有限公司
Brightex Paints (Singapore) Pte. Ltd.
53 Tuas Avenue 1, Singapore 639502
TEL: 6863 5411 FAX: 6863 5411
EMAIL: enquiry53@brightexpaints.com

(Paints Manufacturer & Chemical Industrial Supplier)

Document No.: TDS-SB0020Rev01

Revised Date: 1/Nov/2016

TECHNICAL DATA SHEET FOR

Betex Melamine 185

Description	A two-pack alkyd-melamine based acid curing finish		
Recommended Use	Finishing coat for parquet flooring		
Characteristics	<ul style="list-style-type: none">• Fast Drying• Good chemical resistance• Good scratch resistance• Good durability		
Finish	Gloss/ Satin/ Matt		
Technical Data	Mixing Ratio	: Base	: AC Hardener
		= 10	: 1
	Pot Life (30°C)	: 6 - 8 hour (after dilution with Brightex Thinner)	
	Specific Gravity (25°C)	: 0.99 ± 0.02	
	Flash Point	: 25°C	
Application Data	Application Method	: Spray or Brush	
	Thinner	: Brightex Thinner	
	Dilution	: 10 – 30% by volume	
	Theoretical Coverage	: Approx. 10 m ² /L	
	Dry Film Thickness	: Approx. 20 microns	
	Drying Time (30°C)	Touch Dry	: Approx. 10 – 15 minutes
		Hard Dry	: Approx. 24 hours
Directions of Use	Make sure the parquet floor is dry and clean Sand to ensure a smooth surface and to remove foreign matters before coating. Apply 1 – 2 coat(s) of Betex Melamine Clear 185.		
Packaging	4.5 L		
Storage	Should be tightly sealed and stored in cool, dry place. Keep away from open flames.		
Handling and Safety	As it contains solvent, the product requires special care in handling. Avoid any eye and skin contact. For further information please refer to SDS.		



明達漆業(星)私人有限公司
Brightex Paints (Singapore) Pte. Ltd.
53 Tuas Avenue 1, Singapore 639502
TEL: 6863 5411 FAX: 6863 5411
EMAIL: enquiry53@brightexpaints.com

(Paints Manufacturer & Chemical Industrial Supplier)

Document No.: TDS-SB0020Rev01
Revised Date: 1/Nov/2016

TECHNICAL DATA SHEET FOR

Betex Melamine 185

Disclaimer	The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he/ she wishes to use it. As we have no control over the treatment of the product, the surface preparation, application or other factors affecting the use of the product, we are not responsible for its performance, nor would we accept any liability whatsoever or howsoever arising from the use of the product. The information contained in this data sheet may be modified by us from time to time, and without notice, in light of our experience and product development.
-------------------	--